



PELI-GRAF

Technical Data Sheet

Double Side Corona BOPP Matte Thermal Film

Product	Double Side Corona BOPP Matte Thermal Film		Type	GPMB1210	
Test Items	Test methods	Unit	Data	Note	
Total thickness	GB/T 6672	μm	22.5		
Average thickness deviation		%	-0.96		
Max/Min thickness deviation			2.9/-6.7		
Tensile strength	GB/T 1040	MPa	MD	69	
			TD	120	
Broken elongation		%	MD	123	
			TD	50	
Heat shrinkage	105°C, 30s	%	MD	2.33	
			TD	0.5	
Surface tension	GB/T14216	mN/m	Substrate	40	
			Coating	40	
Peeling Strength	GB/T 8808	N/15mm	0.47		
Bonding Strength	GB/T 8808	N/15mm	4.26		
Haze	GB/T2410	%	75.3		
Friction coefficient	GB 10006	film/film	0.26		