



Soft Touch 3 in 1 Thermal Laminating Film Data Sheet

Product	Soft Touch 3 in 1 Thermal Laminating Film	27 μ	
Items	Test methods	Unit	Data
Total thickness	GB/T 6672	μm	27.73
Average thickness deviation		%	1.23
Max/Min thickness deviation			4.3/-3.7
Tensile strength	GB/T 1040	MPa	MD 75
			TD 126
Broken elongation		%	MD 168
			TD 52
Heat shrinkage	105°C, 30s	%	MD 1
			TD 0.5
Surface tension	GB/T14216	mN/m	Substrate 38
			Coating 38
Haze	GB/T2410	%	72
Friction coefficient	GB 10006	film/film	0.23
Detachment force	GB/T 8808	N/15mm	0.31
Lamination strength	GB/T 8808	N/15mm	4.32

